


Woodbine

Technical Specifications


Style Name	Woodbine
Construction	Multi-Level Loop
Fiber	100% Nylon
Gauge	1/12"
Stitches	11 per inch
Pile Weight	20 OZ/yd ²
Average Pile Height	4 mm±0.5 mm
Backing	PVC with fiberglass
Tile Size	25cm*100cm
Anti-microbial	Health Guard (Available)
Installation Method	



Independent Textile
Testins
Service, Inc.







Ashlar



Herringbone

Performance Specifications

	Test Code	Standard	Test Results		
Flammability Tests					
Radiant Panel	ASTM E 648		Class I	Pass	
Methenamine Pill	ASTM D2859		8	Pass	
Smoke Density	ASTM E 662		≤ 450	Pass	
Stability					
Delamination	ASTM D3936	≥ 3.0 lbc/in	No Separation		
Dimensional Stability	AACHEN	≤ 0.2%	≤ 0.2%	Pass	
Tuft Bind	ASTM D1335	≥ 8.0 lbs	≥ 8.0 lbs	Pass	
Anti-Static					
Static Propensity	AATCC 134	≤ 3.5 kV	≤ 3.5 kV	Pass	
Colour Fastness					
Light	AATCC 16 E	≥ 4-5	4-5	Pass	
Rubbing/Crocking	AATCC 165	≥ 4-5	4-5	Pass	
Wear Tests					
Castor Chair	BS EN 985	r ≥ 2.4	r = 2.8	Pass	
Hexapod Drum	ASTM D5252	≥ 3-4	3.0	Pass	
Generic Tests					
Green Carpet(VOC)	CRI Green Label	GLP 6331 [#] /6330 [#]	Accredited		
Acoustic-Nylon	BS EN ISO 354	Absorption Coefficient-NRC	0.15		

NOTE: All Product Specifications are averages derived from product sample testing and are subject to normal manufacturing tolerances and testing tolerances. Product Specifications may be changed without notice as long as product performance is not materially affected.